



## SP60 - Magic Mirror Glass Technical Data

Transmittance	: 63% - 65%
Reflectance	: 34% - 36%
Coating hardness	: 7H - 9H
Coating material	: TiO <sub>2</sub>
High humidity	: < ± 5% variation of visible transmittance : Meet external appearance standards : 85% humidity at 85°C 100hrs
Thermal cycle	: < ± 5% variation of visible transmittance : Meet external appearance standards : (-40°C/24hrs+85°C/24hrs) 10 cycles
Chemicals test	: Meet external appearance standards : 3% NaOH : 5% neutral detergent : Alcohol : Cleaning: Put the chemicals dot on the coating surface, clean with water after 30 minutes. There is no colour changes and sheds for the coating layer.